



Version 30 x d

Materials group	Material	Material number	DIN	AISI/ASTM/UNS	v _c [SFM]	Q ₁	Q _x	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁
								.0394	.0492	.0591	.0787	.0984	.1181	.1575	.1969	.2362
P	Unalloyed carbon steel R _m < 800 N/mm ²	1.0301	C10	AISI 1010	164 - 328	30xd ₁	-	.0012	.0016	.0020	.0031	.0031	.0039	.0047	.0055	.0063
		1.0401	C15	AISI 1015												
		1.1191	C45E/CK45	AISI 1045												
		1.0044	S275JR	AISI 1020												
		1.0715	11SMn30	AISI 1215												
	Low alloyed steel R _m > 900 N/mm ²	1.5752	15NiCr13	ASTM 3415 / AISI 3310	164 - 328	30xd ₁	-	.0012	.0020	.0024	.0031	.0039	.0047	.0055	.0063	.0071
		1.7131	16MnCr5	AISI 5115												
		1.3505	100Cr6	AISI 52100												
		1.7225	42CrMo4	AISI 4140												
		1.2842	90MnCrV8	AISI O2												
High alloyed tool steel R _m < 1200 N/mm ²	1.2379	X153CrMoV12	AISI D2	131 - 262	30xd ₁	-	.0012	.0020	.0024	.0031	.0039	.0043	.0055	.0063	.0067	
	1.2436	X210CrW12	AISI D4/D6													
	1.3343	HS6-5-2C	AISI M2 / UNS T11302													
	1.3355	HS18-0-1	AISI T1 / UNS T12001													
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000	98 - 197	30xd ₁	-	.0008	.0012	.0016	.0024	.0028	.0039	.0047	.0059	.0071
		1.4105	X6CrMoS17	AISI 430F												
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C	131 - 262	30xd ₁	-	.0012	.0020	.0024	.0031	.0039	.0043	.0055	.0063	.0067
		1.4112	X90CrMoV18	AISI 440B												
	Stainless steel martensitic - PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH												
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH												
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304	98 - 197	5xd ₁	2xd ₁	.0008	.0012	.0016	.0024	.0028	.0039	.0047	.0059	.0071
1.4435		X2CrNiMo 18-14-3	AISI 316L													
1.4441		X2CrNiMo 18-14-3	AISI 316LM													
1.4539		X1NiCrMoCu 25-20-5	AISI 904L													
K	Cast iron	0.6020	GG20	ASTM 30	328 - 656	30xd ₁	-	.0016	.0024	.0031	.0039	.0047	.0059	.0071	.0079	.0098
		0.6030	GG30	ASTM 40B												
		0.7040	GGG40	ASTM 60-40-18												
		0.7060	GGG60	ASTM 80-60-03												



Your contacts



Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Berner Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com

Version 30 x d

Materials group	Material	Material number	DIN	AISI/ASTM/UNS	v _c [SFM]	Q ₁	Q _x	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁	Ød ₁
								.0394 f [IPR]	.0492 f [IPR]	.0591 f [IPR]	.0787 f [IPR]	.0984 f [IPR]	.1181 f [IPR]	.1575 f [IPR]	.1969 f [IPR]	.2362 f [IPR]
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	328 - 656	30xd ₁	-	.0012	.0016	.0020	.0028	.0039	.0047	.0079	.0079	.0079
		3.4365	AlZnMgCu1.5	ASTM 7075												
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	262 - 492	30xd ₁	-	.0012	.0016	.0020	.0024	.0031	.0039	.0047	.0059	.0079
		3.2381	GD-AlSi10Mg	UNS A03590												
	Copper	2.004	Cu-OF / CW008A	UNS C10100	131 - 262	2xd ₁	2xd ₁	.0010	.0014	.0018	.0026	.0031	.0043	.0051	.0063	.0075
		2.0065	Cu-ETP / CW004A	UNS C11000												
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	131 - 262	2xd ₁	2xd ₁	.0010	.0014	.0018	.0026	.0031	.0043	.0051	.0063	.0075
		2.036	CuZn40 CW509L	UNS C28000												
	Brass, Bronze R _m < 400 N/mm ²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	164 - 394	30xd ₁	-	.0014	.0022	.0030	.0039	.0051	.0063	.0071	.0091	.0098
		2.102	CuSn6	UNS C51900												
Bronze R _m < 600 N/mm ²	2.0966	CuAl10Ni5Fe4	UNS C63000	131 - 262	30xd ₁	-	.0010	.0014	.0018	.0026	.0031	.0043	.0051	.0063	.0075	
	2.096	CuAl9Mn2	UNS C63200													
S ₁	Super alloys	2.4856		Inconel 625												
		2.4668		Inconel 718												
		2.4617	NiMo28	Hastelloy B-2												
		2.4665	NiCr22Fe18Mo	Hastelloy X												
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	82 - 164	3xd ₁	1xd ₁	.0002	.0004	.0008	.0012	.0016	.0022	.0028	.0031	.0039
		3.7065	Gr.4	ASTM B348 / F68												
	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	66 - 131	5xd ₁	1xd ₁	.0002	.0004	.0008	.0012	.0016	.0022	.0028	.0031	.0039
9.9367		TiAl6Nb7	ASTM F1295													
S ₃	Cr-Co alloys	2.4964	CoCr20W15Ni	Haynes 25	66 - 131	5xd ₁	2xd ₁	.0002	.0004	.0008	.0012	.0016	.0022	.0028	.0031	.0039
			CrCoMo28	ASTM F1537												
H ₁	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1	98 - 197	5xd ₁	1xd ₁	.0008	.0016	.0024	.0031	.0039	.0047	.0055	.0063	.0071
H ₂	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2												



Your contacts

Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Berner Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com