



Version 40 x d

| Materials group | Material | Material number | DIN | AISI/ASTM/UNS | v _c [SFM] | Q ₁ | Q _x | Ød ₁ .0787 | Ød ₁ .0984 | Ød ₁ .1181 | Ød ₁ .1575 | Ød ₁ .1969 | Ød ₁ .2362 |
|--|--|--------------------|----------------------|-------------------------|-------------------------|-------------------|------------------|--------------------------|--------------------------|--------------------------|--------------------------|--------------------------|--------------------------|
| | | | | | | | | f [IPR] | f [IPR] | f [IPR] | f [IPR] | f [IPR] | f [IPR] |
| P | Unalloyed carbon steel R _m < 800 N/mm ² | 1.0301 | C10 | AISI 1010 | 164 - 328 | 40xd ₁ | - | .0031 | .0031 | .0039 | .0047 | .0055 | .0063 |
| | | 1.0401 | C15 | AISI 1015 | | | | | | | | | |
| | | 1.1191 | C45E/CK45 | AISI 1045 | | | | | | | | | |
| | | 1.0044 | S275JR | AISI 1020 | | | | | | | | | |
| | | 1.0715 | 11SMn30 | AISI 1215 | | | | | | | | | |
| | Low alloyed steel R _m > 900 N/mm ² | 1.5752 | 15NiCr13 | ASTM 3415 / AISI 3310 | 164 - 328 | 40xd ₁ | - | .0031 | .0039 | .0047 | .0055 | .0063 | .0071 |
| | | 1.7131 | 16MnCr5 | AISI 5115 | | | | | | | | | |
| | | 1.3505 | 100Cr6 | AISI 52100 | | | | | | | | | |
| | | 1.7225 | 42CrMo4 | AISI 4140 | | | | | | | | | |
| | | 1.2842 | 90MnCrV8 | AISI O2 | | | | | | | | | |
| High alloyed tool steel R _m < 1200 N/mm ² | 1.2379 | X153CrMoV12 | AISI D2 | 131 - 262 | 40xd ₁ | - | .0031 | .0039 | .0043 | .0055 | .0063 | .0067 | |
| | 1.2436 | X210CrW12 | AISI D4/D6 | | | | | | | | | | |
| | 1.3343 | HS6-5-2C | AISI M2 / UNS T11302 | | | | | | | | | | |
| | 1.3355 | HS18-0-1 | AISI T1 / UNS T12001 | | | | | | | | | | |
| M | Stainless steel ferritic | 1.4016 | X6Cr17 | AISI 430 / UNS S43000 | 98 - 197 | 40xd ₁ | - | .0024 | .0028 | .0039 | .0047 | .0059 | .0071 |
| | | 1.4105 | X6CrMoS17 | AISI 430F | | | | | | | | | |
| | Stainless steel martensitic | 1.4034 | X46Cr13 | AISI 420C | 131 - 262 | 40xd ₁ | - | .0039 | .0047 | .0059 | .0071 | .0079 | .0087 |
| | | 1.4112 | X90CrMoV18 | AISI 440B | | | | | | | | | |
| | Stainless steel martensitic - PH | 1.4542 | X5CrNiCuNb 16-4 | AISI 630 / ASTM 17-4 PH | | | | | | | | | |
| | | 1.4545 | X5CrNiCuNb 15-5 | ASTM 15-5 PH | | | | | | | | | |
| | Stainless steel austenitic | 1.4301 | X5CrNi 18-10 | AISI 304 | 98 - 197 | 5xd ₁ | 2xd ₁ | .0024 | .0028 | .0039 | .0047 | .0059 | .0071 |
| | | 1.4435 | X2CrNiMo 18-14-3 | AISI 316L | | | | | | | | | |
| 1.4441 | | X2CrNiMo 18-14-3 | AISI 316LM | | | | | | | | | | |
| 1.4539 | | X1NiCrMoCu 25-20-5 | AISI 904L | | | | | | | | | | |
| K | Cast iron | 0.6020 | GG20 | ASTM 30 | 328 - 656 | 40xd ₁ | - | .0039 | .0047 | .0059 | .0071 | .0079 | .0098 |
| | | 0.6030 | GG30 | ASTM 40B | | | | | | | | | |
| | | 0.7040 | GGG40 | ASTM 60-40-18 | | | | | | | | | |
| | | 0.7060 | GGG60 | ASTM 80-60-03 | | | | | | | | | |



Your contacts



Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Berner Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com

Version 40 x d

| Materials group | Material | Material number | DIN | AISI/ASTM/UNS | v_c | Q_1 | Q_x | $\varnothing d_1$.0787 | $\varnothing d_1$.0984 | $\varnothing d_1$.1181 | $\varnothing d_1$.1575 | $\varnothing d_1$.1969 | $\varnothing d_1$.2362 |
|---|--|-----------------|--------------------|------------------|-------------------|-------------------|------------------|----------------------------|----------------------------|----------------------------|----------------------------|----------------------------|----------------------------|
| | | | | | [SFM] | | | f [IPR] | f [IPR] | f [IPR] | f [IPR] | f [IPR] | f [IPR] |
| N | Aluminium alloy wrought | 3.2315 | AlMgSi1 | ASTM 6351 | 328 - 656 | 40xd ₁ | - | .0028 | .0039 | .0047 | .0079 | .0079 | .0079 |
| | | 3.4365 | AlZnMgCu1.5 | ASTM 7075 | | | | | | | | | |
| | Aluminium alloy cast | 3.2163 | GD-AlSi9Cu3 | ASTM A380 | 262 - 492 | 40xd ₁ | - | .0024 | .0031 | .0039 | .0047 | .0059 | .0079 |
| | | 3.2381 | GD-AlSi10Mg | UNS A03590 | | | | | | | | | |
| | Copper | 2.004 | Cu-OF / CW008A | UNS C10100 | 131 - 262 | 2xd ₁ | 2xd ₁ | .0026 | .0031 | .0043 | .0051 | .0063 | .0075 |
| | | 2.0065 | Cu-ETP / CW004A | UNS C11000 | | | | | | | | | |
| | Brass lead free | 2.0321 | CuZn37 CW508L | UNS C27400 | 131 - 262 | 2xd ₁ | 2xd ₁ | .0026 | .0031 | .0043 | .0051 | .0063 | .0075 |
| | | 2.036 | CuZn40 CW509L | UNS C28000 | | | | | | | | | |
| | Brass, Bronze $R_m < 400$ N/mm ² | 2.0401 | CuZn39Pb3 / CW614N | UNS C38500 | 164 - 4394 | 40xd ₁ | - | .0039 | .0051 | .0063 | .0071 | .0091 | .0098 |
| | | 2.102 | CuSn6 | UNS C51900 | | | | | | | | | |
| Bronze $R_m < 600$ N/mm ² | 2.0966 | CuAl10Ni5Fe4 | UNS C63000 | 131 - 262 | 40xd ₁ | - | .0026 | .0031 | .0043 | .0051 | .0063 | .0075 | |
| | 2.096 | CuAl9Mn2 | UNS C63200 | | | | | | | | | | |
| S ₁ | Super alloys | 2.4856 | | Inconel 625 | | | | | | | | | |
| | | 2.4668 | | Inconel 718 | | | | | | | | | |
| | | 2.4617 | NiMo28 | Hastelloy B-2 | | | | | | | | | |
| | | 2.4665 | NiCr22Fe18Mo | Hastelloy X | | | | | | | | | |
| S ₂ | Titanium pure | 3.7035 | Gr.2 | ASTM B348 / F67 | 82 - 164 | 3xd ₁ | 1xd ₁ | .0012 | .0016 | .0022 | .0028 | .0031 | .0039 |
| | | 3.7065 | Gr.4 | ASTM B348 / F68 | | | | | | | | | |
| | Titanium alloys | 3.7165 | TiAl6V4 | ASTM B348 / F136 | 66 - 131 | 5xd ₁ | 1xd ₁ | .0012 | .0016 | .0022 | .0028 | .0031 | .0039 |
| 9.9367 | | TiAl6Nb7 | ASTM F1295 | | | | | | | | | | |
| S ₃ | Cr-Co alloys | 2.4964 | CoCr20W15Ni | Haynes 25 | 66 - 131 | 5xd ₁ | 2xd ₁ | .0012 | .0016 | .0022 | .0028 | .0031 | .0039 |
| | | | CrCoMo28 | ASTM F1537 | | | | | | | | | |
| H ₁ | Hardened steel < 55 HRC | 1.2510 | 100MnCrMoW4 | AISI O1 | 98 - 197 | 5xd ₁ | 1xd ₁ | .0031 | .0039 | .0047 | .0055 | .0063 | .0071 |
| H ₂ | Hardened steel ≥ 55 HRC | 1.2379 | X153CrMoV12 | AISI D2 | | | | | | | | | |



Your contacts

Mikron Tool SA Agno
P.O. Box 340
6934 Bioggio
Switzerland
Phone +41 91 610 40 00
Fax +41 91 610 40 10
mto@mikron.com

Mikron GmbH Rottweil
Abteilung Werkzeuge
Berner Feld 71
78628 Rottweil
Germany
Phone +49 741 5380 450
Fax +49 741 5380 480
info.mtr@mikron.com

Mikron Corp. Monroe
P.O. Box 268
200 Main Street
Monroe, CT 06468
USA
Phone +1 203 261 3100
Fax +1 203 268 4752
mmo@mikron.com