

NEW Type A - Finishing


v_c [m/min] | [SFM]
 f_z [mm] | [IPT]

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ⊗ Not recommended




MILLING WITH INTEGRATED COOLING | CUTTING DATA OVERVIEW

Finishing



- ① $a_p = 2 \times d_1$
 $a_e = 0.04 \times d_1$

- ② $a_p = 2 \times d_1$
 $a_e = 0.02 \times d_1$



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	1.0 mm .039"		1/16" 1.5 mm .059"		3/32" 2.0 mm .079"			1/8" 3.0 mm .118"			Ød ₁ 5/32" 4.0 mm .157"			3/16" - 7/32" 5.0 mm .197"			1/4" 6.0 mm .236"			8.0 mm .315"				
					①		②		①		②		①		②		①		②		①		②		①		②	
					v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z	v_c	f_z
P	Unalloyed carbon steel Rm < 800 N/mm²	1.0301	C10	AISI 1010																								
		1.0401	C15	AISI 1015																								
		1.1191	C45E/CK45	AISI 1045	130	0.008	0.009	180	0.012	0.014	200	0.017	0.020	210	0.023	0.026	220	0.025	0.029	220	0.028	0.032	220	0.033	0.038	220	0.038	0.044
		1.0044	S275JR	AISI 1020	427	.00032	.00035	591	.00047	.00055	656	.00067	.00079	689	.00091	.00103	722	.00098	.00114	722	.00110	.00126	722	.00130	.00150	722	.00150	.00173
		1.0715	11SMn30	AISI 1215																								
	Low alloyed steel Rm > 900 N/mm²	1.5752	15NiCr13	ASTM 3415 / AISI 3310																								
		1.7131	16MnCr5	AISI 5115																								
		1.3505	100Cr6	AISI 52100	130	0.007	0.008	180	0.011	0.013	200	0.016	0.018	210	0.022	0.025	220	0.024	0.028	220	0.026	0.030	220	0.029	0.033	220	0.034	0.040
		1.7225	42CrMo4	AISI 4140	427	.00028	.00032	591	.00043	.00051	656	.00063	.00071	689	.00087	.00098	722	.00094	.00110	722	.00102	.00118	722	.00114	.00130	722	.00134	.00157
		1.2842	90MnCrV8	AISI O2																								
High alloyed tool steel Rm < 1200 N/mm²	1.2379	X153CrMoV12	AISI D2																									
	1.2436	X210CrW12	AISI D4/D6	130	0.006	0.007	180	0.010	0.012	200	0.015	0.017	210	0.020	0.023	220	0.021	0.024	220	0.023	0.026	220	0.025	0.029	220	0.030	0.035	
	1.3343	HS6-5-2C	AISI M2 / UNS T11302	427	.00024	.00028	591	.00039	.00047	656	.00059	.00067	689	.00079	.00091	722	.00083	.00094	722	.00091	.00102	722	.00098	.00114	722	.00118	.00138	
	1.3355	HS18-0-1	AISI T1 / UNS T12001																									
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000	130	0.008	0.009	180	0.012	0.014	200	0.017	0.020	210	0.022	0.025	220	0.024	0.028	220	0.026	0.030	220	0.029	0.033	260	0.034	0.040
		1.4105	X6CrMoS17	AISI 430F	427	.00032	.00035	591	.00047	.00055	656	.00067	.00079	689	.00087	.00098	722	.00094	.00110	722	.00102	.00118	722	.00114	.00130	853	.00134	.00157
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C	130	0.008	0.009	180	0.011	0.013	200	0.016	0.018	210	0.022	0.025	220	0.023	0.027	220	0.025	0.029	220	0.028	0.032	260	0.033	0.038
		1.4112	X90CrMoV18	AISI 440B	427	.00032	.00035	591	.00043	.00051	656	.00063	.00071	689	.00087	.00098	722	.00091	.00106	722	.00098	.00114	722	.00110	.00126	853	.00130	.00150
	Stainless steel martensitic – PH	1.4542	X5CrNiCuNb16-4	AISI 630 / ASTM 17-4 PH	130	0.008	0.009	180	0.011	0.013	200	0.016	0.018	210	0.022	0.025	220	0.023	0.027	220	0.025	0.029	220	0.028	0.032	260	0.033	0.038
		1.4545	X5CrNiCuNb15-5	ASTM 15-5 PH	427	.00032	.00035	591	.00043	.00051	656	.00063	.00071	689	.00087	.00098	722	.00091	.00106	722	.00098	.00114	722	.00110	.00126	853	.00130	.00150
	Stainless steel austenitic	1.4301	X5CrNi18-10	AISI 304																								
1.4435		X2CrNiMo18-14-3	AISI 316L	130	0.006	0.007	180	0.008	0.009	200	0.015	0.017	210	0.020	0.023	220	0.022	0.025	220	0.024	0.028	220	0.026	0.030	260	0.032	0.037	
1.4441		X2CrNiMo18-15-3	AISI 316LM	427	.00024	.00028	591	.00032	.00035	656	.00059	.00067	689	.00079	.00091	722	.00087	.00098	722	.00094	.00110	722	.00102	.00118	853	.00126	.00146	
	1.4539	X1NiCrMoCu25-20-5	AISI 904L																									
K	Cast iron	0.6020	GG20	ASTM 30																								
		0.6030	GG30	ASTM 40B																								
		0.7040	GGG40	ASTM 60-40-18	110	0.006	0.007	130	0.012	0.014	150	0.014	0.016	160	0.022	0.025	170	0.025	0.029	170	0.029	0.033	170	0.031	0.036	200	0.036	0.042
		0.7060	GGG60	ASTM 80-60-03	361	.00024	.00028	427	.00047	.00055	492	.00055	.00063	525	.00087	.00098	558	.00098	.00114	558	.00114	.00130	558	.00122	.00142	656	.00142	.00165
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	130	0.009	0.010	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047
		3.4365	AlZnMgCu1.5	ASTM 7075	427	.00035	.00039	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00161	886	.00161	.00185
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	130	0.009	0.010	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047
		3.2381	GD-AlSi10Mg	UNS A03590	427	.00035	.00039	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00161	886	.00161	.00185
	Copper	2.0040	Cu-OF / CW008A	UNS C10100	130	0.010	0.012	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047
		2.0065	Cu-ETP / CW004A	UNS C11000	427	.00039	.00047	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00161	886	.00161	.00185
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	130	0.010	0.012	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047
		2.0360	CuZn40 CW509L	UNS C28000	427	.00039	.00047	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00161	886	.00161	.00185
	Brass, Bronze Rm < 400 N/mm²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	130	0.010	0.012	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047
		2.1020	CuSn6	UNS C51900	427	.00039	.00047	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00162	886	.00161	.00186
Bronze Rm < 600 N/mm²	2.0966	CuAl10Ni5Fe4	UNS C63000	130	0.009	0.010	180	0.013	0.015	200	0.018	0.021	210	0.029	0.033	220	0.030	0.035	220	0.033	0.038	220	0.036	0.041	270	0.041	0.047	
	2.0960	CuAl9Mn2	UNS C63200	427	.00035	.00039	591	.00051	.00060	656	.00071	.00083	689	.00114	.00130	722	.00118	.00138	722	.00130	.00150	722	.00142	.00161	886	.00161	.00185	
S ₁	Super alloys	2.4856		Inconel 625																								
		2.4668		Inconel 718																								
		2.4617	NiMo28	Hastelloy B-2	110	0.004	0.005	120	0.005	0.006	130	0.005	0.006	130	0.008	0.009	140	0.010	0.012	140	0.011	0.013	150	0.012	0.014	160	0.017	0.020
		2.4665	NiCr22Fe18Mo	Hastelloy X	361	.00016	.00020	394	.00020	.00024	427	.00020	.00024	427	.00032	.00035	459	.00039	.00047	459	.00043	.00051	492	.00047	.00055	525	.00067	.00079
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	110	0.008	0.009	120	0.010	0.012	130	0.014	0.016	130	0.020	0.023	140	0.022	0.025	140	0.024	0.028	150	0.026	0.030	160	0.031	0.036
		3.7065	Gr.4	ASTM B348 / F68	361	.00032	.00035	394	.00039	.00047	427	.00055	.00063	427	.00079													