





NEW

# Type A - Semi-finishing

v<sub>c</sub> [m/min]  
f<sub>z</sub> [mm]

RECOMMENDATION FOR USE  
● Excellent | ● Good | ○ Acceptable | ⊗ Not recommended

## MILLING WITH INTEGRATED COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	1.0 mm		1.2 mm		Ød1				2.5 mm		3.0 mm		4.0 mm		5.0 mm		6.0 mm–8.0 mm		
					v <sub>c</sub>	f <sub>z</sub>	v <sub>c</sub>	f <sub>z</sub>	1.5 mm 1/16"	1.8 mm	2.0 mm	2.5 mm 3/32"	3.0 mm 1/8"	4.0 mm 5/32"	5.0 mm 3/16"	6.0 mm–8.0 mm 7/32–1/4"							
P	Unalloyed carbon steel Rm < 800 N/mm <sup>2</sup>	1.0301	C10	AISI 1010	140	0.013	140	0.014															
		1.0401	C15	AISI 1015																			
		1.1191	C45E/CK45	AISI 1045																			
		1.0044	S275JR	AISI 1020																			
		1.0715	11SMn30	AISI 1215																			
	Low alloyed steel Rm > 900 N/mm <sup>2</sup>	1.5752	15NiCr13	ASTM 3415 / AISI 3310	140	0.012	140	0.014															
		1.7131	16MnCr5	AISI 5115																			
		1.3505	100Cr6	AISI 52100																			
		1.7225	42CrMo4	AISI 4140																			
		1.2842	90MnCrV8	AISI O2																			
	High alloyed tool steel Rm < 1200 N/mm <sup>2</sup>	1.2379	X153CrMoV12	AISI D2	140	0.009	140	0.011															
		1.2436	X210CrW12	AISI D4/D6																			
		1.3343	HS6-5-2C	AISI M2 / UNS T11302																			
	1.3355	HS18-0-1	AISI T1 / UNS T12001																				
M	Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000	140	0.014	140	0.015															
		1.4105	X6CrMoS17	AISI 430F																			
		1.4034	X46Cr13	AISI 420C																			
	Stainless steel martensitic	1.4112	X90CrMoV18	AISI 440B	140	0.013	140	0.014															
		1.4542	X5CrNiCuNb16-4	AISI 630 / ASTM 17-4 PH																			
	Stainless steel martensitic – PH	1.4545	X5CrNiCuNb15-5	ASTM 15-5 PH	140	0.013	140	0.014															
		1.4301	X5CrNi18-10	AISI 304																			
	Stainless steel austenitic	1.4435	X2CrNiMo18-14-3	AISI 316L	140	0.010	140	0.012															
1.4441		X2CrNiMo18-15-3	AISI 316LM																				
1.4539		X1NiCrMoCu25-20-5	AISI 904L																				
K	Cast iron	0.6020	GG20	ASTM 30	120	0.009	120	0.019															
		0.6030	GG30	ASTM 40B																			
		0.7040	GGG40	ASTM 60-40-18																			
		0.7060	GGG60	ASTM 80-60-03																			
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	140	0.015	140	0.017															
		3.4365	AlZnMgCu1.5	ASTM 7075																			
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	140	0.015	140	0.017															
		3.2381	GD-AlSi10Mg	UNS A03590																			
	Copper	2.0040	Cu-OF / CW008A	UNS C10100	140	0.017	140	0.019															
		2.0065	Cu-ETP / CW004A	UNS C11000																			
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	140	0.017	140	0.019															
		2.0360	CuZn40 CW509L	UNS C28000																			
	Brass, Bronze Rm < 400 N/mm <sup>2</sup>	2.0401	CuZn39Pb3 / CW614N	UNS C38500	140	0.017	140	0.019															
		2.1020	CuSn6	UNS C51900																			
	Bronze Rm < 600 N/mm <sup>2</sup>	2.0966	CuAl10Ni5Fe4	UNS C63000	140	0.015	140	0.017															
		2.0960	CuAl9Mn2	UNS C63200																			
S <sub>1</sub>	Super alloys	2.4856		Inconel 625	120	0.006	120	0.007															
		2.4668		Inconel 718																			
		2.4617	NiMo28	Hastelloy B-2																			
		2.4665	NiCr22Fe18Mo	Hastelloy X																			
S <sub>2</sub>	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	120	0.014	120	0.015															
		3.7065	Gr.4	ASTM B348 / F68																			
S <sub>3</sub>	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	120	0.014	120	0.015															
		9.9367	TiAl6Nb7	ASTM F1295																			
H <sub>1</sub>	Hardened steel < 55 HRC	2.4964	CoCr20W15Ni	Haynes 25	140	0.006	140	0.007															
			CrCoMo28	ASTM F1537																			
H <sub>2</sub>	Hardened steel ≥ 55 HRC	1.2510	100MnCrMoW4	AISI O1	100	0.009	100	0.010															
		1.2379	X153CrMoV12	AISI D2																			