




CrazyDrill Cool 15 x d - uncoated

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ☒ Not recommended



DRILLING WITH INTERNAL COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	v _c [m/min] [SFM]	Q ₁	Q _x	f [mm/rev] [IPR]																						
								Ød1																						
								0.8 mm .032"	1.0 mm .039"	1.25 mm .049"	1.5 mm .059"	2.0 mm .079"	2.5 mm .098"	3.0 mm .118"	4.0 mm .158"	5.0 mm .197"	6.0 mm .236"													
P	Unalloyed carbon steel Rm < 800 N/mm²	1.0301	C10	AISI 1010	60 197	6xd1	2xd1	0.040 .0016	0.060 .0024	0.090 .0035	0.120 .0047	0.160 .0063	0.180 .0071	0.220 .0087	0.260 .0102	0.280 .0110	0.300 .0118													
		1.0401	C15	AISI 1015																										
		1.1191	C45E/CK45	AISI 1045																										
		1.0044	S275JR	AISI 1020																										
		1.0715	11SMn30	AISI 1215																										
		1.5752	15NiCr13	ASTM 3415 / AISI 3310																										
	Low alloyed steel Rm > 900 N/mm²	1.7131	16MnCr5	AISI 5115	60 197	6xd1	2xd1	0.030 .0012	0.050 .0020	0.080 .0031	0.100 .0039	0.140 .0055	0.160 .0063	0.180 .0071	0.200 .0079	0.220 .0087	0.240 .0094													
		1.3505	100Cr6	AISI 52100																										
		1.7225	42CrMo4	AISI 4140																										
		1.2842	90MnCrV8	AISI O2																										
		1.2379	X153CrMoV12	AISI D2																										
		1.2436	X210CrW12	AISI D4/D6																										
High alloyed tool steel Rm < 1200 N/mm²	1.3343	HS6-5-2C	AISI M2 / UNS T11302	40 131	6xd1	2xd1	0.020 .0008	0.040 .0016	0.060 .0024	0.080 .0031	0.100 .0039	0.120 .0047	0.140 .0055	0.160 .0063	0.180 .0071	0.200 .0079														
	1.3355	HS18-0-1	AISI T1 / UNS T12001																											
	M	Stainless steel ferritic	1.4016														X6Cr17	AISI 430 / UNS S43000												
			1.4105														X6CrMoS17	AISI 430F												
			1.4034														X46Cr13	AISI 420C												
			1.4112														X90CrMoV18	AISI 440B												
1.4542			X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH																										
1.4545			X5CrNiCuNb 15-5	ASTM 15-5 PH																										
Stainless steel martensitic		1.4301	X5CrNi 18-10	AISI 304																										
		1.4435	X2CrNiMo 18-14-3	AISI 316L																										
		1.4441	X2CrNiMo 18-15-3	AISI 316LM																										
		1.4539	X1NiCrMoCu 25-20-5	AISI 904L																										
		Recommended: CrazyDrill Cool - coated																												
		K	Cast iron	0.6020	GG20	ASTM 30																								
0.6030	GG30			ASTM 40B																										
0.7040	GGG40			ASTM 60-40-18																										
0.7060	GGG60			ASTM 80-60-03																										
Recommended: CrazyDrill Cool - coated																														
N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	300 984	5xd1	1xd1	0.030 .0012	0.040 .0016	0.050 .0020	0.065 .0026	0.070 .0028	0.090 .0035	0.110 .0043	0.130 .0051	0.160 .0063	0.190 .0075													
		3.4365	AlZnMgCu1.5	ASTM 7075																										
	Aluminium alloy cast	3.2163	GD-AlSi9Cu3	ASTM A380	200 656	5xd1	1xd1	0.050 .0020	0.060 .0024	0.070 .0028	0.090 .0035	0.110 .0043	0.140 .0055	0.160 .0063	0.190 .0075	0.210 .0083	0.240 .0094													
		3.2381	GD-AlSi10Mg	UNS A03590																										
	Copper	2.004	Cu-OF / CW008A	UNS C10100	100 328	1.5xd1	1xd1	0.035 .0014	0.045 .0018	0.060 .0024	0.070 .0028	0.080 .0031	0.090 .0035	0.100 .0039	0.120 .0047	0.140 .0055	0.180 .0071													
		2.0065	Cu-ETP / CW004A	UNS C11000																										
	Brass lead free	2.0321	CuZn37 CW508L	UNS C27400	140 459	1xd1	0.5xd1	0.035 .0014	0.045 .0018	0.060 .0024	0.070 .0028	0.080 .0031	0.090 .0035	0.100 .0039	0.120 .0047	0.140 .0055	0.180 .0071													
		2.036	CuZn40 CW509L	UNS C28000																										
	Brass, Bronze Rm < 400 N/mm²	2.0401	CuZn39Pb3 / CW614N	UNS C38500	120 394	2xd1	1xd1	0.060 .0024	0.080 .0031	0.090 .0035	0.110 .0043	0.125 .0049	0.140 .0055	0.160 .0063	0.180 .0071	0.190 .0075	0.210 .0083													
		2.102	CuSn6	UNS C51900																										
	Bronze Rm < 600 N/mm²	2.0966	CuAl10Ni5Fe4	UNS C63000	120 394	10xd1	5xd1	0.010 .0004	0.020 .0008	0.030 .0012	0.045 .0018	0.060 .0024	0.080 .0031	0.090 .0035	0.110 .0043	0.130 .0051	0.180 .0071													
		2.096	CuAl9Mn2	UNS C63200																										
S ₁	Super alloys	2.4856		Inconel 625																										
		2.4668		Inconel 718																										
		2.4617	NiMo28	Hastelloy B-2																										
		2.4665	NiCr22Fe18Mo	Hastelloy X																										
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67	20 66	0.5xd1	0.25xd1	0.005 .0002	0.010 .0004	0.025 .0010	0.040 .0016	0.055 .0022	0.070 .0028	0.080 .0031	0.090 .0035	0.110 .0043	0.130 .0051													
		3.7065	Gr.4	ASTM B348 / F68																										
S ₂	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136	20 66	0.5xd1	0.25xd1	0.005 .0002	0.010 .0004	0.025 .0010	0.040 .0016	0.055 .0022	0.070 .0028	0.080 .0031	0.090 .0035	0.110 .0043	0.130 .0051													
		9.9367	TiAl6Nb7	ASTM F1295																										
S ₃	CrCo alloys	2.4964	CoCr20W15Ni	Haynes 25																										
			CrCoMo28	ASTM F1537																										
H ₁	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1																										
		Recommended: CrazyDrill Cool - coated																												
H ₂	Hardened steel ≥ 55 HRC	1.2379	X153CrMoV12	AISI D2																										