




Steel - 50 x d - coated

RECOMMENDATION FOR USE
● Excellent | ● Good | ○ Acceptable | ⊗ Not recommended



DRILLING WITH INTEGRATED COOLING | CUTTING DATA OVERVIEW



Materials group	Material	Mat. no.	DIN	AISI/ASTM/UNS	v _c [m/min]				Q ₁	Q ₂	f [mm/rev]							
					Ød1 ≤ 0.4		Ød1 > 0.4				0.2 mm	0.3 mm	Ød1		0.8 mm	1.0 mm	1.5 mm - 2.0 mm	
					Mid	High	Mid	High			f	f	0.4 mm 1/64"	0.6 mm	1/32"	f	f	
P	Unalloyed carbon steel Rm < 800 N/mm ²	1.0301	C10	AISI 1010														
		1.0401	C15	AISI 1015														
		1.1191	C45E/CK45	AISI 1045	5	40	40	60	2xd1	0.5xd1	0.005	0.010	0.015	0.030	0.040	0.060	0.080	
		1.0044	S275JR	AISI 1020														
		1.0715	11SMn30	AISI 1215														
	Low alloyed steel Rm > 900 N/mm ²	1.5752	15NiCr13	ASTM 3415 / AISI 3310														
		1.7131	16MnCr5	AISI 5115														
		1.3505	100Cr6	AISI 52100	5	25	25	50	2xd1	0.5xd1	0.003 - 0.005	0.008 - 0.010	0.012 - 0.015	0.020 - 0.025	0.035	0.050	0.070	
		1.7225	42CrMo4	AISI 4140														
		1.2842	90MnCrV8	AISI O2														
	High alloyed tool steel Rm < 1200 N/mm ²	1.2379	X153CrMoV12	AISI D2														
		1.2436	X210CrW12	AISI D4/D6														
1.3343		HS6-5-2C	AISI M2 / UNS T11302	5	20	20	35	2xd1	1xd1	0.004	0.008	0.010	0.015	0.025	0.040	0.060		
1.3355		HS18-0-1	AISI T1 / UNS T12001															
M		Stainless steel ferritic	1.4016	X6Cr17	AISI 430 / UNS S43000													
	1.4105		X6CrMoS17	AISI 430F														
	Stainless steel martensitic	1.4034	X46Cr13	AISI 420C														
		1.4112	X90CrMoV18	AISI 440B														
	Stainless steel martensitic - PH	1.4542	X5CrNiCuNb 16-4	AISI 630 / ASTM 17-4 PH														
		1.4545	X5CrNiCuNb 15-5	ASTM 15-5 PH														
	Stainless steel austenitic	1.4301	X5CrNi 18-10	AISI 304														
		1.4435	X2CrNiMo 18-14-3	AISI 316L														
1.4441		X2CrNiMo 18-15-3	AISI 316LM															
1.4539	X1NiCrMoCu 25-20-5	AISI 904L																
K	Cast iron	0.6020	GG20	ASTM 30			50	100										
		0.6030	GG30	ASTM 40B														
		0.7040	GGG40	ASTM 60-40-18	5	40	40	80	2xd1	1xd1	0.005	0.010	0.015	0.020	0.035	0.050	0.070	
		0.7060	GGG60	ASTM 80-60-03														
		N	Aluminium alloy wrought	3.2315	AlMgSi1	ASTM 6351	5	40	60	120	2xd1	1xd1	0.015	0.040	0.050	0.080	0.100	0.120
3.4365	AlZnMgCu1.5			ASTM 7075														
Aluminium alloy cast	3.2163		GD-AlSi9Cu3	ASTM A380	5	40	50	80	2xd1	1xd1	0.015	0.040	0.050	0.080	0.100	0.120	0.150	
	3.2381		GD-AlSi10Mg	UNS A03590														
Copper	2.004		Cu-OF / CW008A	UNS C10100														
	2.0065		Cu-ETP / CW004A	UNS C11000														
Brass lead free	2.0321		CuZn37 CW508L	UNS C27400														
	2.036		CuZn40 CW509L	UNS C28000														
Brass, Bronze Rm < 400 N/mm ²	2.0401		CuZn39Pb3 / CW614N	UNS C38500	5	40	60	100	2xd1	1xd1	0.010	0.030	0.040	0.060	0.080	0.100	0.120	
	2.102		CuSn6	UNS C51900			40	60										
Bronze Rm < 600 N/mm ²	2.0966	CuAl10Ni5Fe4	UNS C63000	5	20	20	40	2xd1	0.5xd1	0.004	0.006	0.010	0.015	0.025	0.040	0.060		
	2.096	CuAl9Mn2	UNS C63200															
S ₁	Super alloys	2.4856		Inconel 625														
		2.4668		Inconel 718														
		2.4617	NiMo28	Hastelloy B-2														
		2.4665	NiCr22Fe18Mo	Hastelloy X														
S ₂	Titanium pure	3.7035	Gr.2	ASTM B348 / F67														
		3.7065	Gr.4	ASTM B348 / F68														
S ₃	Titanium alloys	3.7165	TiAl6V4	ASTM B348 / F136														
		9.9367	TiAl6Nb7	ASTM F1295														
H ₁	Hardened steel < 55 HRC	1.2510	100MnCrMoW4	AISI O1														
		1.2379	X153CrMoV12	AISI D2														